



Feb-09

**Specifications for Swimming Pool Antislip 15**

**Base Fabric: Polyester 2.8x2.8 thread/cm, 1100 Dtex,  
Emboss: Stop**

Properties	Units	Result	Requirements	Test Method
Thickness	mm	1.65	1.5 , $\pm 5\%$	EN 1849-2
Weight	g/m <sup>2</sup>	1720	1700 $\pm 10\%$	EN 1849-2
Width	cm	150, 160	-0.5% , +1%	EN 1848-2
Appearance		Pass	Free from blisters ,cracks ,voids	EN 1850-2
Tensile strength	kg/5cm MD TD	130 124	$\geq 125$ $\geq 110$	EN 12311-2
Elongation	% MD TD	16 15	$\geq 15$ $\geq 15$	EN 12311-2
Tear strength	kg MD TD	27 22	$\geq 18$ $\geq 18$	EN 12310-2
Interlaminar adhesion	kg/5cm	16	$\geq 8$	EN 12316-2
Shear strength of joints	N/50mm		Crack other than at the joint or $\geq$ Tensile strength	EN 12317-2
Straightness	cm	0	$\leq 3$ cm	EN 1848-2
Flatness		0	$\leq 1$ cm	
Dimensional stability	%	0.46	$\leq 0.5\%$	EN 1107-2

*Nurit Naveh*

*R&D Manager*

*HAOGENPLAST Ltd. Plastic Industries. Kibbutz Haogen 42880, ISRAEL  
Tel: 972-9-8980131, Fax: 972-9-8988883*